

Phase 1 and 2 West Graham Drill Program assay results.

Hole ID	From (m)	To (m)	Length (m) ¹	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
WG-23-019	64.00	93.00	29.00	0.39	0.25	0.01	0.04	0.02	0.02	1.36	70
WG-23-020	47.00	91.00	44.00	0.53	0.27	0.02	0.05	0.02	0.02	1.41	100
including	75.00	83.00	7.00	0.75	0.39	0.03	0.06	0.02	0.02	1.86	100
including	87.00	91.00	4.00	1.03	0.62	0.04	0.07	0.05	0.03	2.85	100
WG-23-021	41.00	72.00	31.00	0.46	0.29	0.02	0.06	0.02	0.02	1.50	90
including	42.00	46.00	4.00	0.63	0.46	0.02	0.10	0.03	0.04	2.40	90
including	58.00	63.00	5.00	0.66	0.30	0.02	0.04	0.02	0.01	1.50	90
WG-23-022	61.00	81.00	20.00	0.51	0.26	0.02	0.03	0.01	0.01	1.12	100
including	76.00	80.00	4.00	0.85	0.46	0.03	0.05	0.02	0.02	1.80	100
WG-23-023	45.00	83.00	38.00	0.47	0.28	0.02	0.04	0.02	0.02	1.45	90
including	71.00	82.00	11.00	0.71	0.41	0.02	0.07	0.02	0.04	2.09	90
WG-23-024	29.00	48.00	19.00	0.46	0.25	0.02	0.04	0.01	0.02	1.21	100
and	56.00	61.00	5.00	0.93	0.50	0.03	0.06	0.02	0.02	4.18	100
WG-23-025	20.00	67.00	47.00	0.56	0.30	0.02	0.05	0.02	0.02	1.85	90
including	42.00	65.00	23.00	0.72	0.42	0.02	0.08	0.03	0.03	2.73	90
WG-23-026	106.00	186.90	80.90	0.49	0.25	0.02	0.05	0.02	0.02	1.29	35
including	167.00	186.90	19.90	1.19	0.37	0.04	0.09	0.02	0.02	1.29	35
including	170.00	177.90	7.90	2.48	0.64	0.08	0.15	0.04	0.02	1.82	35
WG-23-027	68.00	120.50	52.50	0.43	0.27	0.01	0.05	0.02	0.02	1.49	85
including	96.65	120.50	23.85	0.57	0.33	0.02	0.06	0.02	0.03	1.79	85
including	111.00	120.50	9.50	0.83	0.37	0.02	0.09	0.03	0.03	2.16	85
WG-23-028	79.00	275.85	196.85	0.32	0.19	0.01	0.04	0.01	0.02	1.07	30
including	89.00	110.00	21.00	0.72	0.18	0.03	0.03	0.01	0.01	0.75	30
including	93.60	95.00	1.40	3.73	0.27	0.17	0.06	0.07	0.01	1.26	30
WG-23-029	84.00	107.00	23.00	0.37	0.25	0.01	0.03	0.02	0.02	1.39	50
WG-23-030	20.00	52.00	32.00	0.60	0.36	0.02	0.07	0.02	0.03	2.02	45
including	39.00	46.00	7.00	0.98	0.54	0.03	0.15	0.38	0.04	3.00	45
WG-23-031	3.00	9.65	6.65	0.37	0.22	0.01	0.04	0.01	0.01	1.08	95
WG-23-032	34.50	42.50	8.00	0.49	0.38	0.02	0.05	0.02	0.03	2.00	85
WG-23-033	38.00	52.00	14.00	0.35	0.24	0.01	0.04	0.02	0.02	1.29	80
WG-23-034	59.00	90.00	31.00	0.27	0.19	0.01	0.04	0.01	0.01	1.26	50
including	96.00	97.65	1.65	0.67	0.34	0.02	0.05	0.03	0.03	2.29	50
WG-23-035	43.00	51.00	8.00	0.26	0.21	0.01	0.04	0.02	0.02	1.25	80
WG-23-036	97.00	102.00	5.00	0.39	0.23	0.01	0.05	0.02	0.01	1.54	45
WG-23-037	147.00	188.65	41.65	0.50	0.34	0.02	0.08	0.02	0.03	1.64	50
including	174.00	188.65	14.65	0.81	0.51	0.02	0.14	0.04	0.05	2.61	50
including	174.00	179.00	5.00	1.21	0.69	0.04	0.14	0.04	0.05	3.32	50
WG-23-038	130.00	140.00	10.00	0.43	0.25	0.01	0.06	0.02	0.21	1.31	75

Hole ID	From (m)	To (m)	Length (m) ¹	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
WG-23-039	191.50	241.00	49.50	0.36	0.28	0.01	0.05	0.02	0.02	1.49	40
including	224.00	241.00	17.00	0.43	0.49	0.01	0.08	0.03	0.04	2.58	40
WG-23-040	169.00	209.00	40.00	0.46	0.32	0.01	0.07	0.02	0.03	1.90	60
WG-23-041	237.00	276.00	39.00	0.43	0.36	0.01	0.17	0.03	0.06	2.04	55
including	243.00	250.00	7.00	0.60	0.49	0.02	0.10	0.03	0.04	2.13	55
including	262.82	275.00	12.20	0.60	0.54	0.02	0.36	0.05	0.11	3.46	55
WG-23-042	256.00	306.00	50.00	1.06	0.34	0.03	0.15	0.04	0.04	1.71	75
including	286.00	306.00	20.00	1.71	0.46	0.05	0.17	0.06	0.06	2.61	75
including	286.90	291.70	4.80	3.15	0.21	0.09	0.15	0.11	0.02	0.95	75
and	331.00	331.40	0.40	6.23	0.30	0.14	0.10	0.12	0.03	2.60	75
and	336.90	337.20	0.30	7.07	0.09	0.15	0.04	0.07	0.01	2.50	75
WG-23-043	212.00	280.00	68.00	0.46	0.36	0.01	0.09	0.02	0.03	1.90	60
including	246.00	280.00	34.00	0.64	0.50	0.02	0.12	0.03	0.04	2.64	60
including	266.00	275.00	9.00	0.94	0.68	0.02	0.19	0.05	0.06	3.83	60
including	277.50	280.00	2.50	0.96	1.02	0.02	0.05	0.04	0.04	4.58	60
and	304.10	304.60	0.50	6.09	0.07	0.12	0.81	0.30	0.03	2.50	60
WG-23-044	362.35	375.40	13.05	0.74	0.81	0.02	0.22	0.05	0.10	4.84	45
including	369.25	375.40	6.15	0.96	1.33	0.03	0.26	0.08	0.18	8.04	45
WG-23-045	286.00	296.00	10.00	0.33	0.24	0.01	0.12	0.02	0.03	1.33	60
and	302.05	304.00	1.95	0.54	0.75	0.02	0.21	0.05	0.11	4.93	60
and	307.55	308.55	1.00	0.81	1.12	0.02	0.31	0.09	0.37	8.50	60
WG-23-046	381.55	402.35	20.80	0.46	0.58	0.01	0.32	0.04	0.14	4.03	65
including	381.55	387.30	5.75	0.51	0.59	0.01	0.76	0.08	0.07	3.79	65
Including	395.30	402.35	7.05	0.89	1.09	0.02	0.29	0.06	0.35	7.63	65
WG-23-047	221.00	271.00	50.00	0.70	0.32	0.02	0.14	0.03	0.04	1.57	80
including	245.00	263.00	18.00	1.27	0.47	0.04	0.20	0.05	0.04	2.16	80
WG-23-048	196.00	229.10	33.10	0.54	0.38	0.02	0.09	0.03	0.03	1.98	85
including	216.00	230.00	14.00	0.76	0.60	0.02	0.14	0.06	0.05	3.03	85
WG-23-049	271.00	302.00	31.00	0.46	0.38	0.01	0.12	0.03	0.04	1.78	70
including	289.00	299.00	10.00	0.69	0.47	0.02	0.16	0.04	0.05	2.10	70
WG-23-050	118.00	143.00	25.00	0.53	0.34	0.02	0.07	0.02	0.03	1.82	85
including	130.00	141.00	11.00	0.76	0.48	0.02	0.10	0.03	0.04	2.56	85
WG-23-051	86.00	111.05	25.05	0.28	0.23	0.01	0.04	0.02	0.02	1.11	100
WG-23-052	174.00	228.00	54.00	0.55	0.29	0.02	0.07	0.02	0.03	1.45	60
including	184.60	208.00	23.40	0.78	0.35	0.02	0.07	0.02	0.02	1.63	60
including	202.50	206.15	3.65	1.24	0.21	0.04	0.11	0.03	0.02	0.92	60
WG-23-053	256.00	259.85	3.85	0.41	0.35	0.01	0.04	0.02	0.02	2.09	90
and	276.75	281.00	4.25	0.49	0.29	0.02	0.08	0.02	0.03	1.62	90
and	294.00	299.00	5.00	0.52	0.35	0.01	0.30	0.06	0.05	2.10	90

Hole ID	From (m)	To (m)	Length (m) ¹	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
WG-23-054	339.00	384.15	45.15	0.38	0.28	0.01	0.18	0.06	0.05	1.74	85
including	348.70	369.00	20.30	0.55	0.38	0.01	0.17	0.04	0.06	2.30	85
WG-23-055	335.00	354.30	19.30	0.36	0.22	0.01	0.09	0.02	0.03	1.00	75
and	382.5	394.00	11.50	0.35	0.25	0.01	0.19	0.03	0.05	0.92	75
WG-23-056	455.00	480.75	25.75	0.47	0.36	0.02	0.15	0.03	0.04	2.01	65
and	485.35	492.00	6.65	0.56	0.46	0.02	0.17	0.04	0.06	2.49	65
WG-23-057	409.00	428.00	19.00	0.41	0.33	0.01	0.09	0.03	0.03	1.67	95
and	447.00	462.00	15.00	0.39	0.28	0.01	0.34	0.07	0.06	0.63	95
and	467.00	468.05	1.05	1.47	0.17	0.04	0.46	0.58	0.09	0.70	95
WG-23-058	327.00	358.00	31.00	0.52	0.37	0.02	0.16	0.03	0.05	2.11	90
WG-23-059	23.00	37.00	14.00	0.53	0.37	0.02	0.04	0.02	0.03	1.95	100
WG-23-060	12.00	42.00	30.00	0.32	0.20	0.01	0.02	0.01	0.01	1.49	100
WG-23-061	14.00	48.00	34.00	0.48	0.24	0.02	0.03	0.01	0.02	1.57	90
including	14.00	26.00	12.50	0.66	0.26	0.02	0.03	0.02	0.01	1.58	90
including	15.60	16.75	1.15	2.07	0.15	0.07	0.03	0.03	0.01	2.17	90
WG-23-062	1.00	21.00	20.00	0.87	0.41	0.03	0.07	0.03	0.05	2.45	90
including	6.50	19.00	12.50	1.07	0.44	0.04	0.08	0.03	0.04	2.20	90
WG-23-063	2.00	61.00	59.00	0.71	0.38	0.02	0.06	0.02	0.02	1.94	50
including	12.00	29.00	17.00	1.01	0.53	0.04	0.06	0.03	0.02	2.39	50
including	40.00	47.00	7.00	1.10	0.49	0.03	0.08	0.03	0.02	2.53	50
WG-23-064	7.00	20.00	13.00	0.35	0.33	0.01	0.06	0.02	0.02	1.90	95
Including	14.20	18.00	3.80	0.77	0.72	0.02	0.14	0.05	0.03	3.66	95
WG-23-065	3.00	15.00	12.0	0.34	0.23	0.01	0.04	0.01	0.02	1.84	70
and	21.40	26.00	4.60	0.31	0.34	0.01	0.09	0.01	0.02	2.44	70
WG-23-066	2.70	16.00	13.30	0.42	0.28	0.01	0.05	0.02	0.02	1.55	95
WG-23-067	3.20	20.00	16.80	0.48	0.30	0.01	0.07	0.02	0.02	1.95	100
including	23.00	26.00	3.00	0.51	0.91	0.02	0.15	0.07	0.10	4.50	100
WG-23-068	23.00	62.00	39.00	0.42	0.33	0.01	0.05	0.02	0.04	1.94	85
including	41.00	46.00	5.00	0.77	0.48	0.03	0.08	0.04	0.04	3.12	85
WG-23-069	112.00	142.00	30.00	0.31	0.24	0.01	0.06	0.02	0.02	1.38	100
WG-23-070	155.00	171.15	16.15	0.37	0.25	0.01	0.06	0.02	0.03	1.31	80
WG-23-071	220.00	250.00	30.00	0.62	0.56	0.02	0.18	0.04	0.06	2.98	80
including	225.00	242.00	17.00	0.82	0.75	0.02	0.20	0.04	0.07	3.94	80
including	237.50	242.00	4.50	1.20	1.75	0.03	0.41	0.08	0.13	9.51	80
WG-23-072	21.00	45.00	24.00	0.53	0.42	0.02	0.06	0.03	0.03	2.27	100
WG-23-073	54.00	151.00	97.00	0.38	0.27	0.01	0.06	0.02	0.03	1.52	50
including	108.00	138.00	30.00	0.53	0.37	0.02	0.09	0.03	0.04	2.03	50
WG-23-074	No significant mineralization										
WG-23-075	136.00	150.00	14.00	0.58	0.47	0.02	0.13	0.03	0.05	3.08	60

Hole ID	From (m)	To (m)	Length (m) ¹	Ni (%)	Cu (%)	Co (%)	Pt (g/t)	Pd (g/t)	Au (g/t)	Ag (g/t)	Estimated True Width %
WG-23-076	224.00	228.00	4.00	0.82	0.28	0.02	0.05	0.02	0.01	8.22	60
WG-23-077	20.70	39.00	18.30	0.29	0.23	0.01	0.02	0.01	0.01	1.24	100
WG-23-078	20.00	49.70	29.70	0.39	0.22	0.02	0.02	0.02	0.01	1.16	85
including	35.00	49.00	14.00	0.47	0.28	0.02	0.03	0.02	0.02	1.46	85
WG-23-079	50.50	57.50	7.00	0.25	0.18	0.01	0.02	0.02	0.01	1.31	100
and	92.00	96.20	4.20	0.29	0.19	0.01	0.02	0.01	0.01	1.02	100
WG-23-080	36.00	40.00	4.00	0.28	0.30	0.01	0.02	0.02	0.02	1.60	90
and	56.00	61.00	5.00	0.29	0.24	0.01	0.02	0.02	0.01	1.53	90
and	67.00	69.85	2.85	0.40	0.28	0.01	0.04	0.02	0.02	2.00	90
and	97.30	98.30	1.00	2.72	0.14	0.12	0.02	0.05	0.01	0.50	90
WG-23-081	185.00	190.00	5.00	0.54	0.38	0.02	0.06	0.09	0.01	2.54	100
WG-23-082	129.00	132.00	3.00	0.43	0.37	0.02	0.03	0.02	0.03	2.43	85
and	168.00	173.00	5.00	0.34	0.25	0.01	0.04	0.02	0.02	1.86	85
WG-23-083	2.35	52.00	49.65	0.60	0.22	0.02	0.05	0.02	0.01	0.94	75
including	12.70	18.20	5.50	1.26	0.20	0.05	0.02	0.02	0.00	0.82	75
including	37.00	52.00	15.00	0.82	0.32	0.02	0.10	0.02	0.02	1.45	75
WG-23-084	52.00	61.00	9.00	0.24	0.17	0.01	0.02	0.01	0.01	0.82	85
WG-23-085	142.00	152.00	10.00	0.50	0.15	0.01	0.05	0.02	0.01	2.29	80

Notes:

1. Length refers to downhole length. Estimated True Width is expressed as a percentage of downhole length. Bold intervals are based on a Ni% grade multiplied by downhole length greater than 15.